

Properties of FHC-42H

HIGASHIYAMA NEW HARDCOAT SERIES

TEST	UNIT	METHOD	RESULT
THICKNESS	μm	—	125
ADHESION		JIS K5400	○ (100/100)
PENCIL HARDNESS	—	JIS K5400 500g	H
STEELWOOL RUBBING		HYNT Method (#0000 200g×10times)	×
HAZE	%	JIS K7136	0.92
TRANSMITTANCE	%	JIS K7136	91.5
CRACK	—	HYNT Method (GAP 3mm)	○

It is not warranty spec.

◆STRUCTURE

