

Properties of FHC-A7WS

HIGASHIYAMA NEW HARDCOAT SERIES

TEST	UNIT	METHOD	RESULT	
THICKNESS	μm		188	
ADHESION		JIS K5400	○ (100/100)	
PENCIL HARDNESS	—	JIS K5400 500g	3H	
STEELWOOL RUBBING		HYNT Method (#0000 200g×10times)	○	
HAZE	%	JIS K7136	7.5	
TRANSMITTANCE	%	JIS K7136	89.9	
CRALITY	%	ASTM D 1003	75.0	
THERMAL SHRINKAGE	MD	%	150°C×1h	0.8
	TD	%	150°C×1h	0.1

It is not warranty spec.

◆STRUCTURE

