

# Properties of FHC-CG2

HIGASHIYAMA NEW HARDCOAT SERIES

TEST	UNIT	METHOD	RESULT	
THICKNESS	$\mu\text{m}$		188	
ADHESION		JIS K5400	○ (100/100)	
PENCIL HARDNESS	—	JIS K5400 500g	3H	
STEELWOOL RUBBING		HYNT Method (#0000 200g×10times)	○	
HAZE	%	JIS K7136	1.7	
TRANSMITTANCE	%	JIS K7136	91.2	
THERMAL SHRINKAGE	MD	%	150°C×1h	0.7
	TD	%	150°C×1h	0.5

It is not warranty spec.

## ◆STRUCTURE

