

Properties of FHC-D3W-W

HIGASHIYAMA NEW HARDCOAT SERIES

TEST	UNIT	METHOD	RESULT
THICKNESS	μm		188
ADHESION		JIS K5400	○ (100/100)
PENCIL HARDNESS	-	JIS K5400 500g	3H
STEELWOOL RUBBING		HYNT Method (#0000 200g × 10times)	○
HAZE	%	JIS K7136	0.2
TRANSMITTANCE	%	JIS K7136	92.0
THERMAL SHRINKAGE	MD	150°C × 1h	0.7
	TD	150°C × 1h	0.5

It is not warranty spec.

◆STRUCTURE

