


# Properties of FHC-M3

HIGASHIYAMA NEW HARDCOAT SERIES

TEST	UNIT	METHOD	RESULT	
THICKNESS	$\mu\text{m}$		188	
ADHESION		JIS K5400	○ (100/100)	
PENCIL HARDNESS	-	JIS K5400 500g	2H	
STEELWOOL RUBBING		HYNT Method (#0000 200g×10times)	○	
HAZE	%	JIS K7136	0.6	
TRANSMITTANCE	%	JIS K7136	90.0	
THERMAL SHRINKAGE	MD	%	150°C×1h	0.8
	TD	%	150°C×1h	0.3

It is not warranty spec.

## ◆STRUCTURE



HIGASHIYAMA FILM CO., LTD.