

# Properties of FHC-S8W

HIGASHIYAMA NEW HARDCOAT SERIES

TEST	UNIT	METHOD	RESULT
THICKNESS	$\mu\text{m}$		188
ADHESION		JIS K5400	○ (100/100)
PENCIL HARDNESS	—	JIS K5400 500g	3H
STEELWOOL RUBBING		HYNT Method (#0000 200g×10times)	○
HAZE	%	JIS K7136	9.0
TRANSMITTANCE	%	JIS K7136	90.0
CRALITY	%	ASTM D 1003	82.0

It is not warranty spec.

## ◆STRUCTURE

