

Properties of FHC-S8W

HIGASHIYAMA NEW HARDCOAT SERIES

| TEST | UNIT | METHOD | RESULT |
|-------------------|---------------|-------------------------------------|----------------|
| THICKNESS | μm | | 188 |
| ADHESION | | JIS K5400 | ○ (100/100) |
| PENCIL HARDNESS | — | JIS K5400 500g | 3H |
| STEELWOOL RUBBING | | HYNT Method (#0000 200g×10times) | ○ |
| HAZE | % | JIS K7136 | 9.0 |
| TRANSMITTANCE | % | JIS K7136 | 90.0 |
| CRALITY | % | ASTM D 1003 | 82.0 |

It is not warranty spec.

◆STRUCTURE

