


Properties of MKZ-T4

HIGASHIYAMA NEW HARDCOAT SERIES

TEST	UNIT	METHOD	RESULT
THICKNESS	μm		188
ADHESION		JIS K5400	○ (100/100)
PENCIL HARDNESS	—	JIS K5400 500g	3H
STEELWOOL RUBBING		HYNT Method (#0000 200g×10times)	○
HAZE	%	JIS K7136	0.4
TRANSMITTANCE	%	JIS K7361	91.4
THERMAL SHRINKAGE	MD	HYNT Method 150°C×1h	0.9
	TD		0.5

It is not warranty spec.

◆STRUCTURE



” Roll-up is possible without masking.”