



片面帯電防止付き高速印刷用透明PETフィルム

Transparent PET film for high speed printing with antistatic on one side.

TEST		UNIT	METHOD	RESULT	
厚み Base Film Thickness		μm	-	100	
ヘイズ Haze		%	JIS K7136	1.0	
全光線透過率 Transmittance		%	JIS K7361	91.1	
密着性 Adhesion		-	JIS K5400	100/100	
破断強度 Tensile Strength	MD	N/mm ²	ASTM D882	217.7	
	TD			220.7	
伸び率 Tensile Elongation	MD	%		173	
	TD			151	
加熱収縮率 Thermal Shrinkage	MD	%		HYNT Method 150°C×30min	0.45
	TD				-0.1
静摩擦係数 Coefficient of Friction		-	HYNT Method (4.4kg Load)	0.3	
動摩擦係数 Kinetic Coefficient of Friction		-	HYNT Method (4.4kg Load)	0.2	
表面抵抗 Surface Resistivity *AS side		logΩ/□	JIS K6911 500V×10sec / 23°C×65%RH	9.0	

* 上記データはいずれも代表値です。It is not warranty spec.

▶ 構成/Structure

帯電防止付き易接着層
/ Easy Adhesion with Anti-static Function

PET

易接着層 / Easy Adhesion for Printing etc.